

Product Description

CapaStone BaseCoat is pure acrylic water based coating consisting of crushed inorganic colored aggregates bound with pure acrylic resin binder used as a base coat for CapaStone paint systems for interior and exterior surfaces.

Recommended Use

Suitable for interior and exterior use on:

Cement plastered walls
Gypsum boards
Ceiling
Concrete
Rendered fair faced brick masonry

Physical Properties

Volume solids	68±2%
Colour	Standard Colours
VOC	8 g/ltr
Thinner/Cleaner	Potable clean water
Packing size	30 kg
Shelf life	24 months

Advantages

Easy to apply, practically odourless and weather proof
Very fine stone size helps achieve a smooth finish for base coat
Resistant to aggressive air pollutants

Test values

VOC content tested and certified by DCL, report no. 2016088756
High water permeability corresponds to class V₂ as per EN1062-1 Value>15g/m²/d
UV stable after 2000hrs of accelerated weathering according to EN ISO 11507
Adhesion to concrete >0.8 N/mm² as per EN 1504-2
Liquid water permeability corresponds to class W₂ as per EN 1062-1 Value≤0.5/kg/m²/h0.5
Class A tested and certified as per ASTM E84

Surface Preparation

Ensure substrate is sound, clean, dry, free of oil, grease, dust, loose particles, laitance and powder paint etc. All loose material must be removed by stiff bristle brushing. Any damaged areas or surface irregularities should be repaired before application. It is most important that substrates are correctly prepared prior to application of paint.

Mixing Paint

CapaStone BaseCoat is a single component water based product, should be mixed properly before application. Can be diluted with potable clean water only.

Theoretical Spread Rate

Dry film thickness	500 - 600 µm
Theoretical coverage*	0.7 - 0.8 m ² /kg

*Spreading rates are indicative, due allowance and wastage factor should be considered in practical application.

Drying Time

Touch dry	2 hours
Dry to over coat*	8 hours

* Drying time generally related to air circulation, temperature, film thickness, no of coats and relative humidity. The given data must be considered as guidelines only. The actual drying time before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. The figures given are typical with: Good ventilation (outdoor exposure or free circulation of air), typical film thickness and relative humidity 70%.

Technical Information No. 0019 – Issue: May 2017

All suggestions and application instructions herein are based on our latest technical experience. Due to the wide variety of individual project conditions, we cannot be held responsible for their content. These instructions do not release the purchaser/applicator/consultant from his responsibility to determine the suitability of the product in consideration of the project characteristics. These instructions are to be considered void when a new edition is released. Our general conditions of sale and delivery in their latest edition apply.

Application Conditions

Substrate temperature should be min.10°C and at least 3°C above the dew point of the air. At application below 10°C drying temperature will be significantly extended and spraying characteristics may be impaired. Paint to be applied to suitable primed surface.

Application Equipment's/Tools

Brush, roller, spraying equipment, peeler, cutter, spirit level, plumb bob, measuring tape, groove tape and chalk liner *

Guiding data for conventional spray equipment:

Gun Type	Hopper Gun
Spray Gun Caliber	8 mm
Spray Angel	90°
Nozzle Size	3 - 6 mm (depends on texture)
Pressure	100 - 120 psi

*The spray details given above are intended as a guide only, fluid hose length, diameter, paint temperature and project complexity all influence the choice of tip and operating pressure.

Typical Paint System

CapaStone BaseCoat can be applied on interior and exterior surface as follows:

Interior and exterior surface standard typical paint system*

	Coats
Stone Prime	1
CapaStone Base Coat	1
Granito/CeraTone/Eurostone	1
NanoClear	2

*Above mentioned paint system is for general guide line only, can be changed as per specification requirements.

Storage and Handling

24 months when stored in warehouse conditions below 35°C in the original, unopened packs. The product must be kept in in cool, dry well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed and always handle with care. Keep out of reach of children.

Health and Safety

Always ensure good ventilation during application and drying. Do not breath vapors or spray when applying paint indoor by spray, wear proper air supplied breathing equipment's. Respiratory equipment's must be suitable for the purpose and meet an appropriates standards. When applying paint, it is advisable to wear suitable eye protection, in case contact with eyes, rinse immediately with plenty of water and seek medical advice. Remove splashes from skin, use soap and water or recognized skin cleaner. Do not use or store by hanging on a hook. Do not empty contents into wadis, drains or watercourses.